



# THE BOMBAY TEXTILE RESEARCH ASSOCIATION

(Approved Body of the Ministry of Textiles, Govt. of India)  
Lal bahadur Shastri Marg, Ghatkopar (West), Mumbai - 400086.  
Phones : 022 - 6202 3636 / 6202 3600

Fax : 91-22-2500 0459 Email : btloffice@btraindia.com / info@btraindia.com  
Website: www.btraindia.com



## BTRA TEST LABORATORIES TEST REPORT

Report Details : <b>BTL/TR/B2507094/FA/1/A/2025</b>	ULR No : <b>TC694125000007094F</b>	Date : <b>25-11-2025</b>
---	------------------------------------	--------------------------

### Anutex Bonded Textiles

Gohit, C4 – 003, Ground Floor, Kanchan Pushpa Complex, Ghodbunder Road,  
Thane  
Maharashtra, Pincode : 400615  
Contact Person : Mrinmoy Mitra

#### THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

Sample No	: <b>B2507094-1</b>	Product Description	: <b>Laminated Polar Fleece Fabric-Colour-PINK, Size-Large</b>
Received on	: <b>05-11-2025</b>	Total Number of Samples in Order	: <b>1</b>
Testing Period	: <b>15.11.2025 TO 25.11.2025</b>	Reference	: <b>Letter dtd.4.11.2025</b>
Despatched on	:	Sample Type	: <b>Fabric</b>
Project Name	:	Page	: <b>1 / 3</b>

### TEST RESULTS

#### Air Permeability (ASTM D 737-18(2023))

Test Parameter	Results
Test Area in cm <sup>2</sup>	38.0
Test Pressure in Pascal	125
ft <sup>3</sup> /ft <sup>2</sup> /sec.	0.0

#### Colour Fastness to Washing [ISO : 105 C10–2006 (A1)] (ISO 105 C10 (A1) : 2006)

Test Parameter	Result
Colour Fastness to Washing at 40°C for 30 min.	.
Change in Colour	4-5
Staining on Adjacent Multi-fiber Fabric	.
Wool	4-5
Acrylic	4-5
Polyester	4-5
Nylon	4-5
Cotton	4-5
Diacetate	4-5

Grey Scale Rating 1-5 : 1 = Very Poor, 2 = Poor, 3 = Fair, 4 = Good, 5 = Excellent.

Saroj Vairagi  
(Authorised Signatory)  
Chemical Testing

Shreyasi Nandy  
(Authorised Signatory)  
Physical Testing

Karishma Hemani  
(Authorised Signatory)  
Eco Testing



# THE BOMBAY TEXTILE RESEARCH ASSOCIATION

(Approved Body of the Ministry of Textiles, Govt. of India)  
Lal bahadur Shastri Marg, Ghatkopar (West), Mumbai - 400086.  
Phones : 022 - 6202 3636 / 6202 3600

Fax : 91-22-2500 0459 Email : btloffice@btraindia.com / info@btraindia.com  
Website: www.btraindia.com



## BTRA TEST LABORATORIES TEST REPORT

Report Details : <b>BTL/TR/B2507094/FA/1/A/2025</b>	ULR No : <b>TC69412500007094F</b>	Date : <b>25-11-2025</b>
---	-----------------------------------	--------------------------

### Anutex Bonded Textiles

Gohit, C4 – 003, Ground Floor, Kanchan Pushpa Complex, Ghodbunder Road,  
Thane  
Maharashtra, Pincode : 400615  
Contact Person : Mrinmoy Mitra

### THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

Sample No	: <b>B2507094-1</b>	Product Description	: <b>Laminated Polar Fleece Fabric-Colour-PINK, Size-Large</b>
Received on	: <b>05-11-2025</b>	Total Number of Samples in Order	: <b>1</b>
Testing Period	: <b>15.11.2025 TO 25.11.2025</b>	Reference	: <b>Letter dtd.4.11.2025</b>
Despatched on	:	Sample Type	: <b>Fabric</b>
Project Name	:	Page	: <b>2 / 3</b>

### TEST RESULTS

#### Colour Fastness to Crocking of Fabric (IS/ISO 105 X12:2016)

Test Parameter	Result
Colour Fastness to Rubbing	.
Staining on Un-dyed Cotton Fabric	.
Dry	4-5
Wet	4-5

Grey Scale Rating 1-5 : 1 = Very Poor, 2 = Poor, 3 = Fair, 4 = Good, 5 = Excellent.

#### Colour fastness to - Water (IS/ISO 105 E01:2013)

Test Parameter	Result
Colour Fastness to Water	.
Change in Colour	4-5
Staining on Adjacent Multi-fiber Fabric	.
Wool	4-5
Acrylic	4-5
Polyester	4-5
Nylon	4-5
Cotton	4-5
Diacetate	4-5

Grey Scale Rating 1-5 : 1 = Very Poor, 2 = Poor, 3 = Fair, 4 = Good, 5 = Excellent.

Saroj Vairagi  
(Authorised Signatory)  
Chemical Testing

Shreyasi Nandy  
(Authorised Signatory)  
Physical Testing

Karishma Hemani  
(Authorised Signatory)  
Eco Testing



# THE BOMBAY TEXTILE RESEARCH ASSOCIATION

(Approved Body of the Ministry of Textiles, Govt. of India)  
Lal bahadur Shastri Marg, Ghatkopar (West), Mumbai - 400086.  
Phones : 022 - 6202 3636 / 6202 3600

Fax : 91-22-2500 0459 Email : btloffice@btraindia.com / info@btraindia.com  
Website: www.btraindia.com



## BTRA TEST LABORATORIES TEST REPORT

Report Details : <b>BTL/TR/B2507094/FA/1/A/2025</b>	ULR No : <b>TC694125000007094F</b>	Date : <b>25-11-2025</b>
---	------------------------------------	--------------------------

### Anutex Bonded Textiles

Gohit, C4 – 003, Ground Floor, Kanchan Pushpa Complex, Ghodbunder Road,  
Thane  
Maharashtra, Pincode : 400615  
Contact Person : Mrinmoy Mitra

### THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

Sample No	: <b>B2507094-1</b>	Product Description	: <b>Laminated Polar Fleece Fabric-Colour-PINK, Size-Large</b>
Received on	: <b>05-11-2025</b>	Total Number of Samples in Order	: <b>1</b>
Testing Period	: <b>15.11.2025 TO 25.11.2025</b>	Reference	: <b>Letter dtd.4.11.2025</b>
Despatched on	:	Sample Type	: <b>Fabric</b>
Project Name	:	Page	: <b>3 / 3</b>

### TEST RESULTS

#### Dimensional Changes in washing and drying ISO 6330 (ISO 6330:2021, ISO 5077:2007, ISO 3759:2011)

Test Parameter	Result
Dimensional Changes, %	.
After 1 wash cycle @40°C	.
Test No.4N Tumble Dry	.
Warp	-0.8
Weft	Nil

-- End of the Report --

Saroj Vairagi  
(Authorised Signatory)  
Chemical Testing

Shreyasi Nandy  
(Authorised Signatory)  
Physical Testing

Karishma Hemani  
(Authorised Signatory)  
Eco Testing



# THE BOMBAY TEXTILE RESEARCH ASSOCIATION

(Approved Body of the Ministry of Textiles, Govt. of India)  
Lal bahadur Shastri Marg, Ghatkopar (West), Mumbai - 400086.  
Phones : 022 - 6202 3636 / 6202 3600  
Fax : 91-22-2500 0459 Email : btloffice@btraindia.com / info@btraindia.com  
Website: www.btraindia.com



## BTRA TEST LABORATORIES TEST REPORT

Report Details : <b>BTL/TR/B2507826/TT/1/A/2025</b>	ULR No : <b>TC69412500007826F</b>	Date : <b>09-12-2025</b>
---	-----------------------------------	--------------------------

### Anutex Bonded Textiles

Gohit, C4 – 003, Ground Floor, Kanchan Pushpa Complex, Ghodbunder Road,  
Thane  
Maharashtra, Pincode : 400615  
Contact Person : Mrinmoy Mitra

### THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

Sample No	: <b>B2507826-1</b>	Product Description	: <b>Laminated Polar Fleece Fabric-Colour-SKY BLUE, SIZE-SMALL</b>
Received on	: <b>05-12-2025</b>	Total Number of Samples in Order	: <b>1</b>
Testing Period	: <b>08.12.2025 TO 09.12.2025</b>	Reference	: <b>Letter dtd.4.12.2025</b>
Despatched on	:	Sample Type	: <b>TT</b>
Project Name	:	Page	: <b>1 / 1</b>

### TEST RESULTS

#### Free Formaldehyde (ISO 14184-1 Analysed by UV Spectrophotometer)

Test Parameter	Result	Method Detection Limit
Free Formaldehyde Content (mg/kg) <i>ND- Not Detected</i>	ND	16.0 mg/kg

-- End of the Report --

Karishma Hemani  
(Authorised Signatory)  
Eco Testing